

IN THE CLAIMS:

Please amend claim 20 as shown below, in which a deleted term is shown with  
strikethrough.

Claims 1-13 (Cancelled).

Claims 14-16 (Withdrawn).

Claims 17-18 (Cancelled).

✓ Claim 19 (Withdrawn).

411 J 613 ✓ Claim 20 (Currently Amended) In a vehicle manufacturing method involving press-forming panel parts from a sheet metal and welding the panel parts together to form an automobile body, the method comprising the steps of:

painting the automobile body so that the automobile is paint-finished;

417 - assembling an engine and functional parts into the paint-finished automobile body to thereby produce an assembled automobile; and

415 inspecting the assembled automobile,

wherein the method further includes, between the painting and the assembling steps,

418 coating a peelable paint on a painted surface of the paint-finished automobile body ~~body~~ to thereby form a protective film on the painted surface, and

at least the assembling step is carried out while the protective film of the peelable paint remains coated on the painted surface of the paint-finished automobile body.

Claims 21-26 (Cancelled).

Claim 27 (Previously Amended) The method of claim 20, further including the steps of:

419 ✓ preliminarily drying said coated peelable paint using a first drying means; and

non-preliminarily drying the preliminarily dried, peelable paint using a second drying means.

Claims 28-29 (Cancelled).

cl9 ✓ Claim 30. (Previously Amended) The method of claim 27, wherein said step of preliminarily drying said peelable paint uses infrared radiation<sup>cl9</sup> from said first drying means and said step of non-preliminarily drying said peelable paint uses hot air<sup>cl1</sup> from said second drying means.

cl37 ✓ Claim 31. (Previously amended) The method of claim 27, further including the step of stabilizing the peelable paint after it is coated on said product and prior to said preliminary drying step.

H 1  
unt  
cl37 ✓ Claim 32. (Original) The method of claim 31, wherein said stabilizing step is performed at room temperature.

cl37 ✓ Claim 33. (Original) The method of claim 27, wherein said preliminary and non-preliminary drying steps are performed at elevated temperatures.

Claims 34-35 (Cancelled).

Claim 36 (Withdrawn).

cl34 ✓ Claim 37. (Original) The method of claim 32, wherein said preliminary and non-preliminary drying steps are performed at elevated temperatures.

cl12 ✓ Claim 38. (Previously amended) The method of claim 20, wherein said peelable paint is water based.

cl12 ✓ Claim 39. (Previously amended) The method of claim 27, wherein said peelable paint is water based.

cl 38 Claim 40. (Previously amended) The method of claim 31, wherein said stabilizing step is performed at an ambient temperature of 15-30 °C and an ambient humidity of 50-80% .

Nelson Claim 41. (Previously amended) The method of claim 27, wherein said preliminary drying step promotes drying of said coated peelable paint from inside the coating, and said non-preliminary drying step dries the preliminarily dried, coated peelable paint from outside the coating.

H1  
cont Nelson Claim 42. (Previously amended) The method of claim 30, wherein said preliminary drying step dries said coated peelable paint from inside the coating, and said non-preliminary drying step dries the preliminarily dried, coated peelable paint from outside the coating.

112  
cl 12  
37, 38 Claim 43. (Previously amended) The method of claim 31, wherein said peelable paint is water soluble and said stabilizing step is performed by allowing the automobile to stand for a sufficiently long time at an ambient temperature of 15-30 °C and an ambient humidity of 50-80% after application of the peelable paint before said preliminary drying step.

cl 8  
44. (Previously amended) The method of claim 20, further comprising the steps of:  
partially drying the peelable paint coated on the painted surface of the paint-finished automobile so as to promote drying of the peelable paint from inside thereof; and  
then finally drying the automobile to uniformly dry the entire peelable paint coated on the painted surface of the paint-finished automobile.

cl 5  
45. (original) The method of claim 20, further including the step of shipping the manufactured vehicle after the inspecting step, wherein said inspecting and shipping steps are carried out while the protective film of the peelable paint remains coated on the assembled automobile body.

Handwritten: *cl 66*  
*could*

46. (Original) The method of claim 20, wherein said protective film formed in said peelable paint coating step has a sufficient thickness to protect said painted surface of the paint-finished automobile body against scratches during said assembling step.

---